

TECHNICAL DATA SHEET

High-tensile steel wire mesh MINAX[®] 80/4 for dynamic ground support applications

z_i ≥ 190 kN/m' *)

 $z_q \ge 70 \text{ kN/m'}$ *)

MINAX [®] high-performance steel wire mesh	
Mesh shape:	rhomboid
Diagonal:	x · y = 102 · 177 mm (+/-3%)
Mesh width:	D _i = 80 mm (+/-3%)
Angle of mesh:	ϵ = 49 degrees
Total height of mesh:	h _{tot} = 15 mm (+/-1 mm)
Clearance of mesh:	h _i = 7 mm (+/-1 mm)
No. of meshes longitudinal:	$n_{I} = 5.6 \text{ pcs/m}$
No. of meshes transversal:	$n_q = 9.8 \text{ pcs/m}$

MINAX [®] steel wire	
Wire diameter:	d = 4.0 mm
Tensile strength:	f _t ≥ 1'770 N/mm²
Material:	high-tensile steel wire
Tensile resistance of a wire:	Z _w = 22.0 kN

MINAX [®] corrosion protection	
Corrosion protection:	GEOBRUGG SUPERCOATING
Compound:	95% Zn / 5% Al
Coating:	min. 150 g/m ²

MINAX [®] mesh standard roll	
Roll width:	b _{Roll} = 2.5 m
Roll length:	I _{Roll} = 15 m
Total surface per roll:	$A_{Roll} = 37.5 \text{ m}^2$
Weight per m ² :	g = 2.6 kg/m ²
Weight per mesh roll:	G _{Roll} = 98 kg
Mesh edges:	mesh ends knotted

htot

hi


MINAX[®] 80/4

Load capacity

Tensile strength of mesh longitudinal:

Tensile strength of mesh transversal:

*) referring to LGA test report 05/2009



Rockfall, slides, mudflows and avalanches are natural events and therefore cannot be calculated. This is why it is impossible to determine or guarantee absolute safety for persons and property with scientific methods. This means that to provide the protection we strive for, it is imperative to maintain and service protective systems regularly and appropriately. Moreover, the degree of protection can be diminished by events that exceed the absorption capacity of the system as calculated to good engineering practice, failure to use original parts or corrosion (i.e., from environmental pollution or other outside influences). L1_MINAX 80 4mm_TechData_171102_2.5mx15m_e.doc Small deviations from the mesh geometry as well as the shape