

## TECHNICAL DATA SHEET

## Rolled Cable Net QUAROX® 0/6.5/275

QUAROX <sup>®</sup> cable net <sup>1)</sup>		
Diagonal:	x · y = 390 · 400 mm (+/- 5%)	
Mesh width:	D <sub>i</sub> = 275 mm (+/- 5%)	
Angle of mesh:	ε = 85 degrees	
No. of meshes longitudinal:	n <sub>i</sub> = 2.5 pcs/m	
No. of meshes transversal:	$n_q = 2.6 \text{ pcs/m}$	

QUAROX® Corrosion protection 2) 3)		
Corrosion protection:	GEOBRUGG SUPERCOATING	
Compound:	95% Zn / 5% Al	
Coating:	min. 150 g/m <sup>2</sup>	

Load capacity	
Tensile strength of net longitudinal:	z <sub>i</sub> ≥ 100 kN/m' <sup>4)</sup>

1)	according	to	ΕN	10223-6
----	-----------	----	----	---------

<sup>2)</sup> according to EN 10244-2


QUAROX <sup>®</sup> Steel wire		
Wire diameter:	$D_w = 3.0 \text{ mm}^{-5}$	
Tensile strength steel wire:	$f_t \ge 1'770 \text{ N/mm}^2$ 6)	
Material:	high-tensile steel wire	
Tensile resistance of a wire:	Z <sub>w</sub> ≥ 12.5 kN	

QUAROX® Steel strand	
Diameter of spiral rope:	D <sub>L</sub> = 6.5 mm
Construction:	1 x 3

QUAROX <sup>®</sup> Net standard roll		
Roll width:	b <sub>Roll</sub> = 3.9 m	
Roll length:	I <sub>Roll</sub> = 30 m	
Total surface per roll:	$A_{Roll} = 117 \text{ m}^2$	
Weight per m <sup>2</sup> :	$g = 1.3 \text{ kg/m}^2$	
Weight per roll:	G <sub>Roll</sub> = 152 kg	
Net edges:	Mesh ends knotted	

<sup>4)</sup> referring to LGA test report 08/2011





Rockfall, slides, mudflows and avalanches are natural events and therefore cannot be calculated. This is why it is impossible to determine or guarantee absolute safety for persons and property with scientific methods. This means that to provide the protection we strive for, it is imperative to maintain and service protective systems regularly and appropriately. Moreover, the degree of protection can be diminished by events that exceed the absorption capacity of the system as calculated to good engineering practice, failure to use original parts or corrosion (i.e., from environmental pollution or other outside influences).

<sup>3)</sup> according to EN ISO 9227

<sup>5)</sup> according to EN 10218

<sup>6)</sup> according to EN 10264-2 / EN 10016-1 and -2