

## TECHNICAL DATA SHEET

# High-tensile Rockfall Protection Netting DELTAX® G80/2

### DELTA<sup>®</sup> high-tensile rockfall protection netting

Mesh shape:	rhomboid
Diagonal:	$x \cdot y = 3.98 \cdot 6.89 \text{ in (+/-5\%)}$
Mesh width:	$D_i = 3.15 \text{ in (+/-5\%)}$
Angle of mesh:	$\epsilon$ ca. 53 degrees
Total height of mesh:	$h_{tot} = 0.31 \text{ in (+/- 0.04 in)}$
Clearance of mesh:	$h_i = 0.16 \text{ in (+/- 0.04 in)}$
No. of meshes longitudinal:	$n_l = 1.74 \text{ pcs/ft}$
No. of meshes transversal:	$n_q = 3.02 \text{ pcs/ft}$

### DELTA<sup>®</sup> steel wire

Wire diameter:	$d = 0.079 \text{ in}$
Tensile strength:	$f_t \geq 256 \text{ ksi}$
Material:	high-tensile steel wire
Tensile resistance of a wire:	$Z_w = 1.2 \text{ kips}$

### DELTA<sup>®</sup> corrosion protection

Corrosion protection:	GEOBRUGG SUPERCOATING <sup>®</sup>
Compound:	95% Zn / 5% Al
Coating:	min. 0.3 oz/ft <sup>2</sup>

### Load capacity


Tensile strength of mesh longitudinal:	$z_l \geq 3.64 \text{ kips/ft}^{1)}$
--	--------------------------------------

<sup>1)</sup> referring to LGA test report 12/2009

### DELTA<sup>®</sup> mesh standard roll

Roll width:	$b_{Roll} = 12.8 \text{ ft}$
Roll length:	$l_{Roll} = 98.4 \text{ ft (on request until 328 ft)}$
Total surface per roll:	$A_{Roll} = 1260 \text{ ft}^2$
Weight per ft <sup>2</sup> :	$g = 0.13 \text{ lbs/ft}^2$
Weight per mesh roll:	$G_{Roll} = 164 \text{ lbs}$
Mesh edges:	mesh ends knotted

DELTA<sup>®</sup> G80/2



Rockfall, slides, mudflows and avalanches are natural events and therefore cannot be calculated. This is why it is impossible to determine or guarantee absolute safety for persons and property with scientific methods. This means that to provide the protection we strive for, it is imperative to maintain and service protective systems regularly and appropriately. Moreover, the degree of protection can be diminished by events that exceed the absorption capacity of the system as calculated to good engineering practice, failure to use original parts or corrosion (i.e., from environmental pollution or other outside influences).